



最頂級 翡翠抗菌人造石
PREMIUM ACRYLIC SOLID SURFACE


純淨系列




A-119 Whale White




A-104 Pure White




A-109 Glacier Peak (透光)




A-103 Natural White



A-210 Light Grey




A-209 Metal Grey



A-111 Espresso



A-115 Deep Sea



A-201 Sunset



A-105 Dark Cave



A-102 Beige Cream

Pure


水晶系列




F-104 Frost Land



F-111 Frost Quartz



ST-009 Snow Range



F-309 Natural Pearl



S-212 Peridot




ST-113 White Limestone



S-110 Cream Sands




F-005 Cirrus




S-207 Milky Sands



S-119 Night Sky



F-218 Velvet




ST-313 Americano

Crystal

水晶系列



F-201 Indian Ocean



S-203 Snow Pearl




S-204 Soft Pearl




S-216 Grey Pearl




S-202 Night Pearl




S-201 Fog



S-111 Tempest Grey




F-103 Concord



ST-116 Soil




F-340 Comet



ST-118 Ballast



F-106 Beige Wales



F-304 Rainy Sky



F-213 Concrete Quartz



F-342 Rosette



F-142 Snow Pile




F-322 Primo




F-303 Sweet Peanut



F-143 Industrial Draft



F-144 Loft Design




F-215 Mojave



S-125 Sicily



F-109 Rocky Mountain




S-309 Cocoa Powder




S-102 Beige Sands



F-105 Gold Twilight



ST-103 Java Brown



F-102 Aquamarine



S-215 Silver Pearl

Crystal



鑽石系列



T-001
Chalcedony



T-004
Alexandrite



T-003
Ambiance




TS-109
Whinstone




TS-121
Ash



MT-001
Grise



MT-012
Tuber Truffle




MT-013
Perigord Truffle




TS-118
Antarctic Snow




TS-116
Latona



TS-202
Apollo



TS-212
Uranos



B-016
Terazzo Bianco



B-017
Terazzo Nero



TS-126
Athens

Diamond








花崗系列




CR-001
Arezzo



CR-003
Salerno




V-900-B
Carrara Lunar




CR-002
Piacenza



V-128-B
Stone Glass



V-129-B
Montana Bound



V-007
Venice



Granite

花崗系列



V-008
Moonscape



V-001
Tijuana




V-020
Solid Rock




V-004
Shell



V-003
Almond



V-016
Pompeii



V-011
Sinai



Granite


花崗系列




V-010
Canyon



V-017
Colosseum



V-019
Moria



V-005
Dark Wood



V-027
Coyote



V-026
Hazelnut



V-025
Black Sea



Granite



最頂級 翡翠抗菌人造石

PREMIUM ACRYLIC SOLID SURFACE

TriStone 台灣總代理

100%
韓國製造

符合美國
國家衛生基金
NSF衛生標準

無毛細孔
不吃色

堅固耐撞


抗UV
不黃變



序號	測試項目	測試細項	測試結果	測試方法
1	抗菌試驗	綠膿桿菌	抗菌值 (R)0.15	JIS Z2801
1-1	抗菌試驗	金色葡萄球菌	抗菌值 (R)0	JIS Z2801
		大腸桿菌	抗菌值 (R)0	JIS Z2801
		肺炎桿菌	抗菌值 (R)0.58	JIS Z2801
		白色念珠菌	抗菌值 (R)0	JIS Z2801
		黑黴菌	等級 0，無霉菌生長	ASTM G21
2	防霉試驗	四松青黴菌	等級 0，無霉菌生長	ASTM G21
		球毛殼菌	等級 0，無霉菌生長	ASTM G21
		綠點帶黴菌	等級 0，無霉菌生長	ASTM G21
		出芽短梗黴菌	等級 0，無霉菌生長	ASTM G21
3	尺寸安定性		0.1%，目視外觀無異狀	CNS 11367
4	彎曲強度		691.6 kgf/cm ²	CNS 4392
5	密度		1.743 g/cm ³	CNS 13333
6	吸水率		0.01%	ASTM D570-98
7	鹽水噴霧試驗		目視外觀無變色	ASTM B117-11
8	線性熱膨脹係數		-30° C~30° C : 37.85 x 10 ⁻⁶	ASTM D696-08
9	光澤度	60°	73%	ASTM D523-08
10	抗壓強度		1258 kgf/cm ²	ASTM D695-10
11	抗曲強度		757.0 kgf/cm ²	ASTM D970-10
12	抗拉強度	5mm/min	547 kgf/cm ²	ASTM D638-10
13	洛氏硬度		HRR 125	ASTM D785-08
14	防焰性		4.1 符合防焰一級規範值	CNS 7614
15	耐化學藥品性	40% 氫氧化鈉	目視無異狀	CNS 4447
		37% 鹽酸	目視有粗造現象	CNS 4447
16	耐磨耗性	500g 1000 轉	重量損失：0.8591g	CNS 10785
17	衝擊強度		2.06 kgf · cm/cm ²	ASTM D256-10
18	耐菸灼性		目視無不可清除之灼痕、退色、龜裂、或起泡等缺點	CNS 11367
19	耐污染性	茶、咖啡、牛奶、食用醋、10% 檸檬酸溶液、95% 乙醇、丙酮	無影響	CNS 11367
20	耐衝擊性		目視無破裂、凹陷等缺點	CNS 11367
21	耐乾熱性		肉眼觀察試片無龜裂、退色或光澤度改變	CNS 11367
22	耐沸水性		質量增加率 0.10% 厚度增加率 0.08% 以肉眼觀察無膨脹、剝離現象	CNS 11367
23	耐刷洗	洗刷次數：2000 次	可耐規定次數的洗淨試驗	CNS 10757
24	耐濕性	100 小時	耐濕性試驗無異常	CNS 11607
25	放射性	RML-OS-02/ 純鍺加馬能譜分析系統	符合綠建材評定原則	GC 3520
26	廢棄物檢驗	萃出液中總銀	ND <0.006(mg/L)	綠建材標準值 0.05(mg/L) NIEA R306.13C
		萃出液中總砷	ND <0.026(mg/L)	綠建材標準值 0.3(mg/L) NIEA R306.13C
		萃出液中總鎘	ND <0.007(mg/L)	綠建材標準值 0.3(mg/L) NIEA R306.13C
		萃出液中六價鉻	ND <0.01(mg/L)	綠建材標準值 1.5(mg/L) NIEA R309.12C
		萃出液中總銅	ND <0.020(mg/L)	綠建材標準值 0.15(mg/L) NIEA R306.13C
		萃出液中總汞	ND <0.0007(mg/L)	綠建材標準值 0.005(mg/L) NIEA R314.12C
		萃出液中總鉛	ND <0.014(mg/L)	綠建材標準值 0.3(mg/L) NIEA R306.13C
27	耐燃性		符合耐燃三級合格標準	CNS 6532



ISO 14001



TEL: 03-355-9119 03-355-8958 FAX: 03-355-4988
E-mail: jadeleadtristone@gmail.com Website: www.jade-lead.com.tw

